

CALCINED PETROLEUM COKE(CPC)

Property	Standard No.	Content (%wt)	Typically (%wt)
Moisture	ASTM D3173-11	Max %0.5	0.4
Volatile Matter	ASTM D3175-17	Max %0.7	0.5
ASH	ASTM D3174-12	Max %0.8	0.6
Sulfur	ASTM D5373-02	Max %0.6	0.5
Fixed Carbon	ASTM D3172-12	Min %97	98

**Size: As Per Customer Requirement
(0-1mm , 1-3mm , 3-5mm , 1-5mm ,...)**

Packing: 10kg Bag / 1 ton Big Bag